

PIK♠ KLARLACK

2K MS 2:1 Clear coat

The PIK KLARLACK MS 2:1 acrylic clear coat is characterized by high flow, good UV resistance (non-yellowing properties) and considerable gloss.

It is recommended for application inside spray booths or other places designed for coating purposes.

It is recommended for surfaces already covered with thinner- and waterborne base coats.

The clear coat is available either in Standard or Express system.



Before applying, clean the surface with silicone remover and let it evaporate. Grind with suitable abrasive paper. Grind recommended for the original layer: P800-P1000 in "wet on wet" system, and P600-800 in dry system. Clean using silicone remover. Always clean and dust the chosen surface with an antistatic cloth.



PIK KLARLACK: 100%
PIK HÄRTER or
PIK HÄRTER Fast: 50%



1,2-1,3 mm



5-10 min
20°C



1,2-1,3 mm



Standard: 9-10 h/20°C
30 min/60°C
Fast: 8-9 h/20°C
20 min/60°C

Article no.	Capacity	Package
59027+59043	1L+0,5L hardener (Standard)	6
59029+59044	5L+2,5L hardener (Standard)	4
59027+59046	1L+0,5L hardener (Fast)	6
59029+59047	5L+2,5L hardener (Fast)	4

Recommended hardener: PIK HÄRTER or PIK HÄRTER Fast

Gloss

Paint spreading

Scratch resistance

Difficulty level of polishing

Viscosity 14-16 s DIN Cup 4mm

Potlife ~1,5 h

The expiry date **PIK KLARLACK:** 12 months
PIK HÄRTER: 6 months

Our application advices, which we gave based on our experience, are given without any engagement from our side. The customer is requested to verify if the product meets his requirements. We cannot be held responsible for other results made by these tests. Formula of this product according to directive 2004/42/EC.