

HT400

2K MS 2:1 Clear coat

The HT400 clear coat does not stream down even form vertical surfaces. It is characterized by expressive color depth and is strongly resistant to scratches.

It guarantees fast drying and evaporating time maintaining perfect gloss, firm hardness and high resistance.

The clear coat hardens quickly providing thick top coating which is highly resistant to ultraviolet radiation.



Before applying, clean the surface with silicone remover and let it evaporate. Grind with a suitable abrasive paper. Grind recommended for the original layer: P800-P1000 in "wet on wet" system, and P600-800 in dry system. Clean using silicone remover. Always clean and dust the chosen surface with an antistatic cloth.



HT400: 100%
THU+: 50%
TVA: 25%



1,3-1,6 mm



5-7 min
20°C



1,3-1,6 mm



12-14 h/20°C
30 min/60°C

Article no.	Capacity	Package
59348+59378	0,5L+0,25L hardener	6
59025+59005	1L+0,5L hardener	6
59026+59007	5L+2,5L hardener	4

Recommended hardener: THU+

The product should be mixed with TVA thinner (up to 25%)

Gloss

Paint spreading

Scratch resistance

Difficulty level of polishing

Potlife 1-1,5 h

The expiry date **HT400:** 12 months
THU+: 6 months

Our application advices, which we gave based on our experience, are given without any engagement from our side. The customer is requested to verify if the product meets his requirements. We cannot be held responsible for other results made by these tests. . Formula of this product according to directive 2004/42/EC.