

4444

2K UHS 2:1 Clear coat

The clear coat is designed to achieve significantly firm hardness. Excellent for spots repairs as well as whole car body painting. Is highly resistant to scratches and ultraviolet radiation and provides long-lasting gloss.

Easy to apply. It is characterized by good flow and does not create any damp patches.

The clear coat provides fast-hardening and solid thick top coating.



1st step: Before applying, clean the surface with silicone remover and let it evaporate.

2nd step: Grind with a suitable abrasive paper. Grind recommended for the original layer: P800-P1000 in "wet on wet" system, and P600-800 in dry system.

3rd step: Clean using silicone remover.

4th step: Always clean and dust the chosen surface with an antistatic cloth.



4444: 100%
TH-01: 50%
TVU: max 10%



1,3-1,4 mm



5-7 min
20°C



1,3-1,4 mm



12-14 h/20°C
30 min/60°C

| Article no. | Capacity | Package |
|-------------|------------------|---------|
| 59021+59448 | 1L+0,5L hardener | 6 |
| 59022+59012 | 5L+2,5L hardener | 2 |

Recommended hardener: TH-01

The product should be mixed with TVU thinner up to 10%

Gloss 

Paint spreading 

Scratch resistance 

Difficulty level of polishing 

Viscosity 15-17 s DIN Cup 4mm

Potlife 4-6 h

The expiry date **4444:** 24 months
TH-01: 6 months

Our application advices, which we gave based on our experience, are given without any engagement from our side. The customer is requested to verify if the product meets his requirements. We cannot be held responsible for other results made by these tests. Formula of this product according to directive 2004/42/EC.