

## ZP

### Polyester resin

It is an elastic and structural resin with additional catalysers. Together with fiberglass mat it is suitable for manual repairs of mayor holes and other imperfect parts of car bodies. Perfect for repairs of car bodies, caravans, boats as well as yachts. The finishing layer is characterized by great adhesion and high resistance to petrol, grease, oils, diluted acids, alkalis and high temperature (up to 120 °C).



The products has good adhesion to various surfaces. It can be applied on metal, steel, aluminum, polyester laminates as well as wood. The polyester resin also provides good adhesion to acrylic primers and old coating layers.

Sand (grind) and clean the metal surface beforehand.

In case of steel substrates, degrease, dry

sand (P80-120) and degrease again .

The aluminum surfaces should be degreased, dulled with the abrasives and degreased again.

In relation to wood, remove all traces of dust and other impurities.

The primed surfaces as well as old coating layers should be degreased, dry sanded (P220-P280) and degreased again.



**Resin:** 100%

**Hardener:** 2-3% (in set)



Mix the ingredients thoroughly to achieve homogenous color



Potlife: 10-15 min



It can be applied in several layers.



21°C: 35-45 min

Article no.	Capacity	Color
59104	1kg	light yellow
59105	5kg	

#### Advice

Prepare a suitable piece of fiberglass mat, in such way that it expands the edges of damaged place up to 2 cm. Mix with the hardener and apply on previously cleaned surface with a paintbrush. Put the mat on the spots, and using the paintbrush apply pressure on the mat to help it soak. Several layers can be applied. Wait up to 45 min either before mechanical processing in case of laminates surface or before smoothing with spraying putty. Minimum application temperature is 10. Application in temperature lower than 20 extends the drying time.

#### Caution

Do not fill the can with remained and already mixed resin.

#### Efficiency

6-8 m<sup>2</sup>/L (50µm layer)

#### The expiry date

12 months

*Our application advices, which we gave based on our experience, are given without any engagement from our side. The customer is requested to verify if the product meets his requirements. We cannot be held responsible for other results made by these tests. . Formula of this product according to directive 2004/42/EC.*